



Concure M-V Epoxy System

Product Name:

Concure M-V Epoxy System
Product ID: 250

Manufacturer:

Concure Products Inc
3220 West Sixth Street
Chester, PA 19013
Ph: 610-497-0198
Toll Free: 800-925-7746
Email: info@concureproducts.com

Description:

Concure M-V Epoxy System is a reactive, two-component, moisture mitigation coating to stop moisture and vapor emissions on existing concrete. Concure M-V Epoxy System has minimal odor and does not contain solvents. Concure M-V Epoxy System reduces moisture vapor emission rate of 25 pounds to less than 3 pounds per the ASTM F1869 Calcium Chloride Test. Concure M-V Epoxy System reduces moisture vapor permeability from 8.6 Perms to less than 0.1 Perms per ASTM E96 Wet Method Test and meets the ASTM F3010 test requirements.

Concure M-V Epoxy System is formulated in the following versions:

- #1. **Quick Cure** curing in less than one hour
- #2. **Fast Cure** curing in four hours
- #3. **Standard Cure** curing in 16 hours

Advantages:

- Zero VOC
- Adjustable curing times
- Superior bonding
- Fast installation of floor covering
- Can be used in adverse weather conditions
- Can cure as low as 40°F (4.4°C)
- Reduces MVER from 25 lbs. to below 3 lbs.
- Solvent free

Can be used as primer for coatings
Non-blushing
Does not contain Silicone
Low Viscosity
Install flooring in 6 to 26 hours
CaCl₂ less than 1 lb.

Applications:

Concure M-V Epoxy System is a topical moisture and vapor remediation coating over any concrete substrate. Concure M-V Epoxy System can be used over new concrete as a primer for reducing surface pH.

Technical:

Component A: Color: Colorless
Component B: Color: Yellow to Amber
Mixed Color: Straw to Pale Yellow
Mixed Viscosity: 800 to 1300 + or - cps
MVER Calcium Chloride: 24.6# to 2.2# in 1 day
(ASTM F1869)* 24.6# to 1.1# in 3 days
*Standard Cure Version
WVT Perm Testing: 0.06 Perms
(ASTM E96)

Technical:

Bond Strength: 390psi (concrete failure)
(ASTM D4541)

Product	Pot Life	Cure Time	Install cement patch and installation window *	Install coating	Thickness
Quick	8 min	20 min	Up to 10 min after cure	Soon as dry	14 mils
Fast	20 min	4 hours	Up to 4 hrs? after cure	Soon as dry	14 mils
Standard	40 min	16 hours	Up to 24 hrs after cure	Soon as dry	14 mils

Above chart is based on 72°F temperature, 50% relative humidity. As with all epoxies, increase in temperatures accelerates the cure times; Cooler temperatures extend cure times.

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Concure Products Inc., to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Concure Products quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY Concure Products, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Concure M-V Epoxy System

Limitations:

Do not install if air or substrate temperature is below 40°F (4.4°C) or above 95°F (35°C). Concrete should be at least 5 days old for installation. If concrete is less than 5 days old, call for technical installation instructions. Do not install if concrete slab has excessive wetness or ponding water.

Shelf Life: 6 Months

Storage: Store between 40°F and 80°F (5°C and 25°C) to prevent clouding and crystallization. Do not allow to freeze.

Packaging:

Quick cure: 1-gallon unit
Fast cure: 1 and 2.5-gallon units
Standard: 2-1/2 gallon and 5-gallon units
All units are prepackaged for convenient installation.

Preparation:

Concrete must be shot blasted or grinded to eliminate any curing agents, coatings, adhesives or surface contamination. Concrete surface must be prepared to reflect a profile of ICRI CSP 3 - 5. Once surface prep is completed, surface must be vacuum cleaned to remove all dust.

Cracks and Joints:

All cracks, joints and saw cuts should be opened with a crack chaser and vacuum cleaned. Patch with Concure 401 Crack Fill Cement System.

Expansion Joints:

See architect or general contractor for design and instruction.

Installation Thickness:

Concure M-V Epoxy System is a coating that should be installed at 14 mils minimum thickness, approximately 110 square feet per

gallon. This can be accomplished in one 14 mil application or two applications of 7 mils each. If you need more than 48 hours to apply a cementitious topping, use the 2 - application method and apply sand to the second application.

Mixing & Application:

NOTE: For best application properties, units should be acclimated between 60°F and 70°F (15°C and 20°C) if possible. Mix **Part A to Part B** together for 3 minutes at 400 rpm. Prevent any action that entraps air while mixing. Ensure materials at the bottom and sides of the mixing container are agitated. Pour Concure M-V Epoxy System mix onto the concrete floor. Use a squeegee to slowly spread epoxy at a rate of 110 sq. ft. per gallon. Back roll with a 3/8" nap roller and evenly distribute the material to release air. Let cure to touch. Material should be clear when dry.

If floor covering is your final finish:

If patching or leveling is required prior to flooring covering installation, a Styrene Acrylic Primer should be used within the specified installation window prior to applying a self-leveling, skim coat or feather-type compound. Patching and leveling can begin when Concure M-V Epoxy System turns clear and slightly tacky without transfer. Cure times vary. A test area is always recommended with the primer and underlayment prior to installation.

Observe Dew Point when installing coatings or floor covering. Do not install flooring or coatings if the surface of Concure M-V Epoxy System is wet.

You must be within the window for application of cement based patching and leveling materials.

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Concure Products Inc., to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Concure Products quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY Concure Products, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Concure M-V Epoxy System

For Quick cure system: Window for installation of patching compounds is 10 minutes after epoxy cures.

For Fast cure system: Window for installation of patching compound is 60 minutes (TABLE STATES 4 HOURS) after epoxy cures.

For Standard system: Window for installation of patching compound is 24 hours after epoxy cures.

If epoxy coating is your final finish:

You can use the Concure M-V Epoxy System as a primer for your coating systems. Concure M-V Epoxy System is compatible with 100 percent solid and solvent based systems.

Warranty:

Extended Warranties are available. Written extended warranties are available on a per job basis. Please call for information.

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Concure Products Inc., to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Concure Products quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY Concure Products, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.