



**Concure
Products Inc.**

Concure Flooring Sealant

Product Name:

Concure Flooring Sealant
Product ID: 100

Manufacturer:

Concure Products Inc
3220 West Sixth Street
Chester, PA 19013
PH: 610-497-0198
Toll Free: 800-925-7746
info@concureproducts.com

Description:Concure Flooring Sealant is a water based, pre-mixed liquid designed to penetrate deep into the concrete slab. Concure Flooring Sealant is designed to stop hydrostatic pressure and reduce vapor permeability to protect surface applied coatings and adhesives from the effects of capillary moisture and vapor pressure. The organic and inorganic composition of Concure Flooring Sealant penetrates to become an integral part of the concrete slab leaving no surface film or residue.

The Concure Flooring Sealant permanently forms an internal capillary break preventing positive, negative and horizontal moisture intrusion. Concure Flooring Sealant also forms an internal membrane film further sealing the capillary system from moisture migration and water vapor emissions to provide maximum protection. Concure Flooring Sealant is a white, low viscosity liquid that requires no special handling or equipment.

Advantages:

- Low Odor/Solvent Free/VOC Compliant
- Fast drying
- Deep penetration
- Improved bonding
- Fast installation of floor covering
- Water clean up
- Can be used above and below grade concrete
- Stops concrete from dusting
- Controls high PH
- Improves surface strength

Can take foot traffic once dry
Same day

Applications:

Concure Flooring Sealant is applied to fresh/green or existing concrete for waterproofing, vapor emission reduction, sealing and weatherproofing substrates.

Concure Flooring Sealant protects floor coverings such as resilient, epoxy, carpet, rubber tile, wood, laminate, cement toppings and other sheet materials from disbonding failure due to concrete slab moisture.

Technical:

Appearance:	Milky white to off-white
Odor:	Slight Characteristic
Flammability:	Non-Flammable
Viscosity:	200 cps
VOC:	5 grams/L
Weight per gallon:	8 pounds 15 ounces
Tensile strength:	435 psi Controlblock
ASTM D7234	490 psi @300 sq.ft. block
Permeability:	9.4# Control
ASTM F1869	2.3# @300 sq.ft./gallon
Absorption:	11.3% Control mortar
ASTM C413 B	4.2% @300 sq.ft./gallon
Re-Coat Time:	20 to 30 Minutes
Minimum Dry Time:	36 Hours for Mat Test
Foot Traffic:	Approximately 6 hours
MVER Reduction	CaCl2

1 coat: 11.9# to 1.51# in 1 day

2coats: 17.91# to 2.49# in 2 days

Limitations:

Do not allow Concure Flooring Sealant to freeze in shipment or storage. Do not apply Concure Flooring Sealant if air or substrate temperature is below 50°F or above 95°F. Applications must be protected if rain or freezing temperatures are expected within 24 hours after application. Concrete substrate must be clean, sound and free of all foreign matter. Green concrete must be

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Concure Products Inc., to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Concure Products quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY Concure Products, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Concure Flooring Sealant

properly finished as instructed. Aged concrete must be properly prepared. Do not apply to concrete with standing water on the surface. Do not allow water to pool on the application for the first 24 hours. Do not sand or grind concrete after Concure Flooring Sealant application.

Site Testing:

ASTM F1869 testing of Aged Concrete is conducted prior to floor preparation or Concure Flooring Sealant application.

Please call for technical assistance if moisture vapor emissions are greater than 25 pounds.

Preparation:

Aged Concrete must be shot blasted using a 330 shot. Curing agents or any other foreign matter must be removed. Sand or small aggregates must be visible (ICRI surface profile CSP 3 – 5). Grinding with a diamond grinder can be used. Diamond blades should be #20 diamonds. Thoroughly vacuum surface after preparation.

Cracks and Joints:

All cracks, joints and saw cuts should be opened with a crack chaser and vacuum cleaned. Then, apply Concure 401 Crack Fill Cement System.

Expansion Joints:

Consult with the architect or general contractor for design and instruction.

Mixing & Application:

Mix Concure Flooring Sealant with a 250 to 400 RPM drill and mixing paddle before using. Do not add anything to thin or entrain air during mixing. A two coat concrete surface application of Concure Flooring Sealant is recommended using a low pressure sprayer.

Fresh/Green Concrete:

Concure Flooring Sealant is applied to Green Concrete as soon as the concrete can be walked

upon without damage and surface water is not visible. Approximately 6 to 12 hours in typical conditions. Initial application rate is 300 to 400 square feet per gallon. Do not pond Concure Flooring Sealant or oversaturate the fresh concrete surface.

After sweeping or vacuuming the concrete surface, a second Concure Flooring Sealant

application is applied at 300 to 400 square feet per gallon after 7 days for optimum performance. Constantly broom any puddles until Concure Flooring Sealant is absorbed into the slab.

Aged Concrete:

A two coat Concure Flooring Sealant application is recommended to properly prepared Aged Concrete. The initial application rate is approximately 300 square feet per gallon. Absorption rates vary depending on the porosity of the concrete. Evenly distribute Concure Flooring Sealant with a broom to remove excess material and puddles.

The first application should be damp and absorbed in 20 to 30 minutes. After the first coat has been absorbed, but not dry, a second application is applied at a rate of 300 to 400 square feet per gallon. Constantly broom any puddles of Concure Flooring Sealant.

Subsequent Testing:

Aged concrete applications of Concure Flooring Sealant must dry at least 36 hours after application before mat testing. Cool, damp, high humidity conditions may extend time before initiating moisture testing.

Fresh / Green concrete applications of Concure Flooring Sealant must dry at least 36 hours after the second application (7 Days) before mat testing. Cool, damp, high humidity conditions may extend time before initiating moisture testing.

Test area must be acclimated to conditions intended for installation and use at least 24 hours prior to conducting ASTM F710-11, Section X2.3

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Concure Products Inc., to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Concure Products quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY Concure Products, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Concure Flooring Sealant

Mat Testing for moisture. Do not sand or grind area.

Ensure the mat testing remains in place and undisturbed for 72 hours for proper evaluation.

ASTM F1869 Calcium Chloride testing and ASTM F2659 Electronic Moisture Meter testing are found to be inaccurate at this stage.

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Concure Products Inc., to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Concure Products quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY Concure Products, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.